SPRAYMATE® SUPER ETCH® PRIMER

TM5.70

Description

- A premium, single pack epoxy etch primer.

Product Characteristics

- Excellent adhesion to all common metals.
- Excellent anti-corrosive properties.
- Ideal for touch-up repairs on equipment.
- May be overcoated with Spraymate Rapid Enamel.

Colours and Gloss

- Black and grey – satin.

Recommended Film Thickness (Per Coat)

	Typical
Dry film thickness (µm)	20
Wet film thickness (µm)	200

Basic Data at 25°C

Solids content approx.	10% by volume
Touch dry after	5 minutes
Dry to handle	20 minutes
Hard dry	1 hour
Minimum recoat time	1 hour
Maximum recoat time	3 months

Surface Preparation

- All surfaces to be coated must be clean, dry and free from dust, oil and grease.
- Substrate temperature should be at least 3°C above dew point.
- Relative humidity should not exceed 85% during application and before the dry to handle time.

MILD STEEL

- Remove all rust and any loose material by wire brush or mechanical sander

NON FERROUS METALS, STAINLESS STEEL, GALVANISED IRON, ZINCALUME®, COLORBOND®:

- Abrade using Scotch-Brite® pad or wet and dry sandpaper.
- Do not use steel wool.

PREVIOUS SUITABLE COAT

- Mechanically sand with P220-240 grit sandpaper.

Application Instructions

- Agitate by shaking the can for at least 2 minutes after the pellet starts to rattle.
- Apply 2-3 double coats and allow 5 minutes flash off between coats.
- Adequate ventilation must be continuously maintained during application and curing.
- Cleanup with mineral turpentine.
- For recommendations outside those contained in this data sheet, refer to Wattyl.

Application Notes

- When spraying aerosols, apply multiple light coats to avoid runs, begin and end coats beyond the edge of the item being sprayed.
- Aerosols have an optimum operating temperature between 15-30°C, use outside this temperature range may inhibit spray efficiency.
- Try to avoid spraying in cold and high humidity conditions.
- Ensure the aerosol is shaken thoroughly before use.
- Spray at a distance of 30cm from the object to be sprayed and use slow even strokes.
- After spraying, invert the aerosol and spray until clear gas escapes to avoid blockages.

Safety Precautions

- Flammable. Avoid contact with heat and naked flame.
- Do not puncture or incinerate can, even when empty.
- Avoid contact with skin and eyes.
- Use gloves, mask and goggles during application.
- Provide adequate ventilation when using in confined spaces.
- This product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the safety data sheet (SDS).

Precautions

- Adhesions to most automotive plastics is generally good, but should be cross-checked.
- Please test this product to determine if it is suitable for the required end-use.
- For recommendations outside those contained in this data sheet, refer to Wattyl.

SPRAYMATE® SUPER ETCH® PRIMER

TM5.70

Product Compatibility

PRIMERS – N/A

TOPCOATS

- Spraymate Rapid Enamel

Storage and Packaging

- Shelf life at least 12 months in an unopened container.
- All components shall be stored in a dry internal environment at between 5°C and 35°C.
- Packaging: 400g aerosol
- Product line: 1560

For the most up to date information, please visit our website at www.wattylpc.com.au, or contact us at Australia 132 101 (Australia) 0800 825 7727 (New Zealand).

ZINCALUME and COLORBOND are registered trademarks of Bluescope Steel Limited. Scotch-Brite is a registered trademark of 3M Company. All other Trademarks are the property of Hempel (Wattyl) Australia Pty Ltd.

1. This information, provided by Hempel (Wattyl) Australia Pty Ltd is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Wattyl's warranties express and implied. Wattyl advises that you (a) review the Product Data Sheets (PDS) and Safety Data Sheets (SDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Wattyl and the product(s) be transported, stored and handled in accordance with the information on the SDS and relevant PDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.
2. The information in this PDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl does not warrant that the information provided is current when the product is used or is wholly comprehensive.
3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl office before using the product(s).
4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Wattyl's Technical Services shall be contacted prior to commencement. Trademarks are the property of Hempel (Wattyl) Australia) Pty Ltd. (ABN 40 000 035 914)

Wattyl Protective Coatings is part of the Hempel Group, a world leading supplier of trusted coating solutions. Hempel is a global company with strong values, working with customers in the decorative, marine, infrastructure and energy industries. Our purpose is to shape a brighter future with sustainable coating solutions, and with more than 100 years of protecting some of our customer's most valuable assets, we aim to earn their trust every day. The Hempel Group is proudly owned by the Hempel Foundation.