

PURPOSE

This section describes non-ferrous metal surface preparation methods. Method selection will be based on the type of metal, condition of the metal, application experience, budget and condition of the current coating system.

INTRODUCTION

To obtain the best results from a paint system the best possible surface preparation consistent with the degree of sophistication of the system is required. The quality of the paint and surface preparation (i.e. removal of oxides, scale, salts, grease, dirt and loose paint) are the most important factors in determining the lifetime of the paintwork, and therefore the length of time the surface will be protected. First class preparation has the potential to extend the protective life of any paint system.

There are often several surface preparation methods available – dependant on type of surface. The method selected will depend on a number of factors including environmental conditions and cost.

The cost of proper surface preparation may seem expensive but the benefits of extended coating life and reduced maintenance costs will almost always, more than offset any additional surface cleaning cost.

SURFACE CONTAMINANTS

Oil, Grease Fat and Perspiration

Oil, grease, fat and perspiration deposits cannot be removed by mechanical methods of cleaning. The simplest method of removal is to use a solvent emulsifiable degreaser or biodegradable detergent. Apply the degreaser liberally to the contaminated surface, allow to stand for a short time, then hose off with fresh potable water. Besides liquid solvent degreasing, other methods include:

- Solvent vapour cleaning.
- Alkaline cleaning.
- Biodegradable detergent.

Please refer to AS 1627.1 Metal Finishing – Preparation and Pre-treatment of Surfaces - Removal of Oil, Grease and Related Contamination.

SURFACE PREPARATION NON-FERROUS METAL

A range of other metals can be coated with protective coatings provided the required surface preparation is undertaken. The required surface preparations for galvanised steel, aluminium, stainless steel, cast iron, Zincolume[®], hot metal spray and Colorbond[®] are described in the following section.

GALVANISED STEEL

Dry Abrasive Blast

Lightly abrasive blast using a non-metallic grit, to achieve a roughened, uniform flat appearance over the entire surface. Care should be taken not to remove excessive zinc as this will reduce the corrosion protection. Clean the surface to remove all preparation residue.

Wet Abrasive Blast

Lightly wet abrasive blast using a non-metallic grit, to achieve a roughened, uniform flat appearance over the entire surface. High pressure water wash using clean, fresh potable water to remove all blasting residue.

Power Tool Clean

Mechanically abrade the entire surface to achieve a roughened, uniform flat appearance. DO NOT use a wire brush as this will tend to polish rather than abrade the surface. Clean the surface to remove all preparation residue.

ALUMINIUM

Dry Abrasive Blast

Use a lightly abrasive blast using a non-metallic grit to achieve a uniform, flat appearance over the entire surface profile of 35 – 50 microns. Clean the surface to remove all preparation residue.

Wet Abrasive Blast

Lightly wet abrasive blast using a non-metallic grit to achieve a roughened, uniform flat appearance over the entire surface. High pressure water wash using clean, fresh water to remove all blasting residue.

Power Tool Clean

Mechanically abrade the entire surface using 40-80 grit paper/disc for below and above the waterline. Clean the surface to remove all preparation residue.

Etching Solution

Liberal apply a commercially available aluminium etching solution (typically acid based). Allow the surface to react (a whitening may result) but do not allow to dry. Clean off using copious quantities of clean, fresh potable water to remove all the etching solution.

Note: These types of materials are hazardous and highly corrosive. Please refer to the suppliers MSDS regarding their proper use and handling.

STAINLESS STEEL

Dry Abrasive Blast

Abrasive blast using a non-metallic grit to achieve a uniform, flat appearance over the entire surface, and a surface profile of 35 – 50 microns. Clean surface to remove all preparation residue.

Wet Abrasive Blast

Wet abrasive blast using a non-metallic grit to achieve a uniform, flat appearance over the entire surface, and a surface profile of 35 – 50 microns. High pressure wash using clean, fresh potable water to remove all blasting residue.

Power Tool Clean

Mechanically abrade the surface using 80 grit paper/disc. Clean the surface to remove all preparation residue.

ZINCALUME[®]

Degrease and then lightly sand the surface. For maximum adhesion, allow the surface to weather for 3 – 6 months prior to painting. Clean the surface to remove all preparation residue.

HOT METAL SPRAY

Clean the surface using high pressure water wash.

COLORBOND[®]

Degrease and clean the surface to remove all residue.



Quality
ISO 9001

The Business is committed to quality in the design, production and delivery of its products and services. The Australian manufacturing facilities quality management systems are certified to ISO9001.

The Business' laboratory facilities are accredited for technical competence with the National Association of Tests Authorities, Australia (NATA) and comply with the requirements of ISO/IEC 17025. Accreditation No.104 (Footscray) and 931 (Kilburn).



For the most up to date information contact Wattyl Customer Care or visit the Wattyl Website.

**CUSTOMER CARE HOTLINE
WEBSITE**

**Australia
132 101
www.wattylpc.com**

**New Zealand
0800 735 551
www.wattylpc.com**

Trademarks are the property of Valspar Paint (Australia) Pty Ltd.

1. This information, provided by Valspar Paint (Australia) Pty Ltd (hereinafter referred to as "Valspar"), is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Valspar's warranties express and implied. Valspar advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Valspar and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Valspar endeavours to update this information and maintain the accuracy and currency of its contents, Valspar does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Valspar recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Valspar office before using the product(s). 4. To the full extent permitted by law, Valspar's liability for breach of a condition or warranty implied into the contract for sale between Valspar and you by law is limited at Valspar's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Valspar Technical Services shall be contacted prior to commencement. VALSPAR PAINT (AUSTRALIA) PTY LTD (ABN 40 000 035 914)