



COLOURTHANE® S-SERIES TOPCOAT

TM9.32

DESCRIPTION

- an ultra-premium, two-part isocyanate cured, satin polyester polyurethane finish for interior timber

PRINCIPAL CHARACTERISTICS

- offers high build with excellent edge-coverage plus outstanding feel and appearance
- fast stack-ability, especially when using hardener fast
- exhibits a tough, flexible film when fully cured
- excellent flow and levelling
- soft feel satin finish
- superior colour reproducibility through intermix tinting system
- ideal for interior timber surfaces where superior appearance and resistance to wear is required, such as kitchen cabinets, panelling, furniture, shop fittings etc
- range of hardeners and thinners available to provide flexibility in application
- resistant to splash and spillage of common household chemicals such as nail polish, vegetable oil and alcoholic beverages etc.

Note: We advise that you test this product to determine if it is suitable for your particular use.

COLOURS AND GLOSS

- satin - 30% gloss
- Watty Colour Designer®, Laminex®, Formica and Wilsonart colours, AS2700 colours
- can be formulated to provide customers with their own corporate colour ranges

BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY

- vehicle type polyester polyurethane
- mix ratio 2A:1B by volume
- typical film thickness (per coat) 25-35 microns (dry), 55-80 microns (wet)
- solids content approx. 45% by volume
- theoretical spreading rate 18 m²/L for 25 microns (dry)

Mixed with Colourthane S-Series Standard Part B (for other Part B's refer to tables below)

- dust free 20-30 minutes
- print free 2 hours
- pot life 6 hours (20% thinner)
- full cure after 7 days
- recoat time refer to instructions for use
- shelf life (cool, dry place) at least 12 months in unopened container

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- all surfaces must be free from wax, silicone, oil and other contaminants
- fill holes and minor imperfections with Watty Full Stop Timber Putty
- sand smooth with 180-240 grade fre-cut paper, and remove all sanding dust
- filling/sealing, apply 1-2 coats of Colourthane UC210 Timber Undercoat or Colourthane PE420 Polyester Undercoat, sand smooth with 320- 400 grade paper, remove all sanding dust
- the appearance of the top-coat depends on the smoothness of the filler/sealer, so care at this stage is of utmost importance
- Colourthane S-Series can be applied to suitable existing finishes, provided they are degreased and sanded
- laminates (eg. melamine); mechanically sand with 320-400 grade abrasive
- relative humidity should not exceed 75% during application and before the dry to handle time



INSTRUCTIONS FOR USE

- mixing ratio by volume: 2A:1B
- cure with Colourthane S-Series hardeners only
- induction time - none
- potlife at 25°C thinned 20% - 6 hours (standard Part B), 3 hours (fast Part B), 9 hours (hardener slow). Do not use after this time even if the mix is still liquid
- potlife is reduced by reducing the thinner quantity, refer to additional data for more information
- stir the components and mixed product well using a mechanical mixer
- choose the hardener suited to the ambient temperature, use of other hardeners may result in minor gloss variation due to increased or decreased set up time
- apply two coats by conventional spray
- generally, spray vertical surfaces with a wide fan, building up thin, wet coats, allowing 5-10 minutes flash off time between coats (at 25°C), for horizontal surfaces, higher film-builds may be applied
- recoating is not usually necessary however leave the product overnight for optimal results
- may be recoated, without sanding, up to 16 hours after the first application
- if re-coating is necessary after this time, sand lightly with 800-1200 grade wet or dry between coats
- however care should be taken not to apply excessive builds in a single coat as solvent boil may occur especially in warmer conditions
- do not apply or attempt to cure at temperatures below 10°C
- relative humidity should not exceed 75% during application and before the dry to handle time
- **Warning:** Excessive builds on timber can lead to stress-cracking as the timber adjusts to its new conditions of temperature and moisture content. The recommended maximum total build is 150 microns (dry film) for the total system.
- for recommendations outside those contained in this data sheet, refer to WattyL

APPLICATION

- **AIRLESS and AIIR-ASSISTED AIRLESS SPRAY**
 - not recommended
- **AIR SPRAY**
 - recommended thinner Colourthane Reducer or Thinner L748
 - volume of thinner up to 20%
 - nozzle orifice 1.2 - 1.6 mm
 - nozzle pressure 210 - 350 kPa(30 - 50 psi)
- **HVLP CONVENTIONAL**
 - recommended thinner Colourthane Reducer or Thinner L748
 - volume of thinner up to 20%
 - fluid nozzle 1.2 - 1.6 mm
 - pressure to the gun..... 250 - 350 kPa (30 - 50 psi)
 - pressure to air cap 70 kPa (10 psi)
- **CLEANING SOLVENT** Colourthane Reducer or Thinner L748
- **Note:** In warmer conditions, replace some or all of Colourthane Reducer Standard with Colourthane Reducer Slow or Thinner L748 (extra slow). In colder conditions, replace some or all of the Colourthane Reducer Standard with Colourthane Reducer Fast.



COLOURTHANE® S-SERIES TOPCOAT

TM9.32

REDUCER GUIDE

	15°C and below	20°C	25°C	30°C	35°C and above
Colourthane Reducer Fast					
Colourthane Reducer Standard					
Colourthane Reducer Slow					
Thinner L748 (extra slow)					

- thinning recommendations are given as a guide and may vary depending upon substrate temperature and weather conditions

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- contains 0.084% monomeric diisocyanate when mixed. Provide adequate ventilation during use. Breathing the vapour is dangerous. Avoid prolonged breathing of fumes. Where ventilation is poor or where applied by spray, use suitable respiratory equipment at all times
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

ADDITIONAL DATA

CURING AGENT GUIDE

- choose the hardener suited to the ambient temperature, use of other hardeners may result in minor gloss variation due to increased or decreased set up time

	15°C and below	20°C	25°C	30°C	35°C and above
Colourthane Part B Fast					
Colourthane Part B Standard					
Colourthane Part B Slow					
Thinner L748					

Curing table - using Standard Part B

Substrate temperature	Dust free	Tack free	Dry to handle	Ready to sand	Hard dry
15°C	30 min	50 min	3 hr	6 hr	7 days
25°C	20 min	30 min	2 hr	4 hr	7 days
35°C	10 min	20 min	1 hr	2 hr	7 days

Curing table - using Fast Part B

Substrate temperature	Dust free	Tack free	Dry to handle	Ready to sand	Hard dry
15°C	20 min	30 min	2 hr	4 hr	7 days
25°C	10 min	20 min	1 hr	2 hr	7 days
35°C					

Curing table - using Slow Part B

Substrate temperature	Dust free	Tack free	Dry to handle	Ready to sand	Hard dry
15°C					
25°C	30 min	50 min	3 hr	6 hr	7 days
35°C	20 min	30 min	2 hr	4 hr	7 days

- adequate ventilation must be continuously maintained during application and curing



COLOURTHANE® S-SERIES TOPCOAT

TM9.32

Pot life when mixed with 20% thinner

Paint temperature	Standard Part B	Fast Part B	Slow Part B
15°C	9 hr	6 hr	
25°C	6 hr	3 hr	9 hr
35°C	3 hr		5 hr

Pot life when mixed with 10% thinner

Paint temperature	Standard Part B	Fast Part B	Slow Part B
15°C	6 hr	3 hr	
25°C	3 hr	1½ hr	6 hr
35°C	1½ hr		3 hr

PACKAGING

Tinters 4 litres

Part A 1 litre, 4 litres, 20 litres

Part B 1 litre, 2 litres

For the most up to date information contact Wattyl Customer Service Hotline or visit the Wattyl Website.

CUSTOMER SERVICE HOTLINE
WEBSITE

Australia
132 101
<http://www.wattyl.com.au>

New Zealand
0800 735 551
<http://www.wattyl.co.nz>

Wattyl, Colourthane and Super Etch are registered trademarks of Wattyl Australia Pty Ltd. Laminex is a registered trademark of The Laminex Group Pty. Ltd.

1. This information is important to ensure that the listed Wattyl product(s) perform according to the stated application and uses and must be followed to meet Wattyl's warranties express and implied. Wattyl advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Wattyl and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl office before using the product(s). 4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Wattyl Technical Services shall be contacted prior to commencement. WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)