



DESCRIPTION

- a fast-drying industrial enamel with hammer pattern

PRINCIPAL CHARACTERISTICS

- quick-drying, with an excellent “hammer” pattern
- designed for interior and exterior use
- for finishing sheet-metal work, castings, office equipment, and machinery where a heavy-duty, but decorative effect is required e.g. lawn-mower frames, tool-boxes, trailers etc

Note: We advise that you test this product to determine if it is suitable for your particular use.

COLOUR AND GLOSS

- Silver, gloss
- Silver (tint base) tintable to selected colours (refer Hammer finish colour guide)

BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY

- vehicle type modified co-polymer resin
- typical film thickness (per coat) 25 microns (dry), 85 microns (wet)
- solids content approx. 30% by volume
- theoretical spreading rate 12m²/L for 25 microns (dry)
- touch dry..... 10 minutes
- dry-to-handle..... 20 minutes
- hard dry 24 hours
- recoat time minimum 1 hour
- shelf life (cool, dry place) at least 12 months in unopened container

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- best coating performance will be obtained with the highest degree of surface preparation
- degrease thoroughly to remove all oil, grease and other surface contaminants
- mild steel; remove all rust and any loose material by wire brush or mechanical sander, degrease, prime with Watty! All Purpose Primer
- non-ferrous metals, galvanised iron, ZINCALUME®, COLORBOND®; abrade using a Scotch-Brite® pad or wet and dry sandpaper. Do not use steel wool. Degrease, prime with Watty! Super Etch® Primer
- suitable previous coat; mechanically sand with P220-240 grit sandpaper
- substrate temperature should be at least 3°C above dew point
- relative humidity should not exceed 85%

INSTRUCTIONS FOR USE

- stir thoroughly with a flat-bladed or mechanical stirrer before, and during use
- paint temperature must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in low sag resistance and slower cure
- for conventional or airless spray, apply a mist coat, followed by a single full coat
- adequate ventilation must be continuously maintained during application and curing
- for recommendations outside those contained in this data sheet, refer to Watty!



APPLICATION

- **AIRLESS SPRAY**
 - recommended thinner L700 Industrial Enamel Thinner
 - volume of thinner up to 10%
 - nozzle orifice..... approx 0.33mm (0.013 inch)
 - nozzle pressure 12 Mpa (1700 psi)
 - apply a mist coat, followed by a full single coat

- **AIR SPRAY**
 - recommended thinner L700 Industrial Enamel Thinner
 - volume of thinner up to 20%
 - nozzle orifice 1.4 - 1.8 mm
 - nozzle pressure 350 - 450 kPa (50-60 psi)
 - apply a mist coat, followed by a full single coat

- **CLEANING SOLVENT** L700 Industrial Enamel Thinner

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- reaction of the contents with moisture may result in a pressure build up on storage. Place a cloth over the lid and open carefully to release pressure and avoid splashing
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

PACKAGING

4 litres, 20 litres

For the most up to date information contact WattyL Customer Service Hotline or visit the WattyL Website.

	Australia	New Zealand
CUSTOMER SERVICE HOTLINE	132 101	0800 735 551
WEBSITE	http://www.wattyL.com.au	http://www.wattyL.co.nz

WattyL and Super Etch are registered trademarks of WattyL Australia Pty Ltd. ZINCALUME® and COLORBOND® are registered trademarks of Bluescope Steel Limited. Scotch-Brite is a registered trademark of the 3M Company.

1. This information is important to ensure that the listed WattyL product(s) perform according to the stated application and uses and must be followed to meet WattyL's warranties express and implied. WattyL advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by WattyL and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While WattyL endeavours to update this information and maintain the accuracy and currency of its contents, WattyL does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, WattyL recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest WattyL office before using the product(s). 4. To the full extent permitted by law, WattyL's liability for breach of a condition or warranty implied into the contract for sale between WattyL and you by law is limited at WattyL's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required WattyL Technical Services shall be contacted prior to commencement. WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)