

DESCRIPTION

- a two pack isocyanate-free catalysed acrylic antigraffiti clear coating

PRINCIPAL CHARACTERISTICS

- contains silicone additives to resist graffiti damage and assist with graffiti removal
- the clear coating creates a barrier and minimises shadowing
- unlimited recoatability
- excellent gloss off the gun
- fast drying
- excellent exterior durability
- good chemical and solvent splash resistance
- will cure down to 5 °C
- isocyanate-free
- use as protective clear coating over Paracryl IF540 colours and metallic

COLOURS AND GLOSS

- Clear - full gloss

RECOMMENDED FILM THICKNESS (PER COAT)

	Minimum	Maximum	Typical
Dry film thickness microns	35	35	35
Wet film thickness microns	90	90	90
Theoretical spreading rate m ² /l	11.4	11.4	11.4

BASIC DATA AT 25 °C

- solids content approx..... 40% by volume
- mix ratio 4A:1B by volume
- touch dry after 30 minutes
- full cure 7 days
- temperature resistance 95 °C (dry), 35 °C (wet)

SURFACE PREPARATION

PREVIOUS SUITABLE COAT

- must be dry and free from chalking and contamination and sufficiently roughened if necessary
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning
- substrate temperature must be at least 5°C during surface preparation, application and curing and at least 3°C above dew point.
- relative humidity should not exceed 85%

APPLICATION INSTRUCTIONS

- mixing ratio by volume 4A:1B
- mix Paracryl IF540 Antigraffiti Clear Part A with Paracryl IF540 Part B only
- induction time - none
- pot life at 25 °C 8 hours. Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer

- this product must be thinned with the recommended thinner before application
- thinning recommendations are given as a guide and may vary depending upon substrate temperature and weather conditions
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- Valspar recommends the use of coating inspection reports in compliance with AS/NZS 3894.10,11,12 refer to Information Sheet I-20 for more information
- for recommendations outside those contained in this data sheet, refer to Valspar

APPLICATION METHODS

• **AIRLESS SPRAY**

- recommended thinner Thinner L747
- volume of thinner 10-20%
- nozzle orifice approx. 0.38mm (0.015 inch)
- nozzle pressure 15 MPa (2100 psi)

• **AIR SPRAY**

- recommended thinner Thinner L747
- volume of thinner 15-25%
- nozzle orifice approx. 1.4-1.8mm
- nozzle pressure 0.3-0.4 MPa (50-60 psi)

At temperatures greater than 30 °C, or in windy conditions, or where slower drying is required, part, or all, of Thinner L747 may be replaced with Thinner L748. However, film thicknesses must be closely monitored as excessive film builds may result in sagging

• **BRUSH/ROLLER**

- recommended thinner Thinner L754
- volume of thinner 5-10%
- The maximum dry film thickness that can be achieved when brushing/rolling is 30 microns
- Multiple coats may be required to achieve the recommended dry film thickness

• **CLEANING SOLVENT**..... Thinner L747

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

ADDITIONAL DATA

Graffiti Removal

- Paracryl IF540 Antigrffiti Clear has the ability to withstand repeated graffiti removal after achieving full cure
- apply a commercially available graffiti remover, suitable for painted surfaces in conjunction with the manufacturers recommendations. Lightly rub the surface affected until graffiti is removed. For more difficult areas use a soft bristled brush
- wash down surface to remove any residue from the graffiti removal process
- best results are obtained by removing graffiti within a few days
- caution should be taken to limit the exposure of Paracryl IF540 Antigrffiti Clear to these removal products as extended contact and repeated use may cause a hazy/low gloss appearance and result in the need to reapply more Paracryl IF540 Antigrffiti Clear
- if some shadowing can not be removed by the above methods then it will be necessary to lightly sand the surface to remove the shadowing and re apply an additional coat of Paracryl IF540 Antigrffiti Clear

Overcoating Table

Minimum and maximum overcoating intervals with Paracryl IF540 Antigrffiti Clear

Interval	5 °C	15 °C	25 °C	35 °C
Min	2 hrs	1 hr	30 mins	15 mins
Max	Unlimited when dry and free from chalking and contamination			

Curing and Potlife Table

Paint temperature	5 °C	15 °C	25 °C	35 °C
Touch Dry	2 hrs	1 hr	30 mins	15 mins
Dry to Handle	72 hrs	32 hrs	16 hrs	12 hrs
Full Cure	28 days	14 days	7 days	5 days
Potlife (at application viscosity)		12 hrs	8 hrs	4 hrs

- adequate ventilation must be continuously maintained during application and curing

PRECAUTIONS

- for recommendations outside those contained in this data sheet, refer to Valspar

PRODUCT COMPATIBILITY

Primers

- Paracryl IF540 (colours)
- Paracryl IF540 Metallic

Topcoats

- Paracryl IF540 Anti Graffiti Clear

STORAGE AND PACKAGING

- shelf life at least 12 months
- all components shall be stored in a dry internal environment at between 5 °C and 35 °C
- packaging 5 Litre Kit (4 Litre Part A, 1 Litre Part B)
- product line: 2017



Quality
ISO 9001

Valspar is committed to quality in the design, production and delivery of its products and services. Valspar's Australian manufacturing facilities quality management systems are certified to ISO9001.

Valspar's laboratory facilities are accredited for technical competence with the National Association of Tests Authorities, Australia (NATA) and comply with the requirements of ISO/IEC 17025. Accreditation No.104 (Footscray), 1154 (Glendenning) and 931 (Kilburn).



For the most up to date information contact Valspar Customer Service Hotline or visit the Wattyl Website.

**CUSTOMER SERVICE HOTLINE
WEBSITE**

**Australia
132 101
www.wattylpc.com**

**New Zealand
0800 735 551
www.wattylpc.com**

Trademarks are the property of Valspar Paint (Australia) Pty Ltd.

1. This information, provided by Valspar Paint (Australia) Pty Ltd (hereinafter referred to as "Valspar"), is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Valspar's warranties express and implied. Valspar advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Valspar and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Valspar endeavours to update this information and maintain the accuracy and currency of its contents, Valspar does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Valspar recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Valspar office before using the product(s). 4. To the full extent permitted by law, Valspar's liability for breach of a condition or warranty implied into the contract for sale between Valspar and you by law is limited at Valspar's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Valspar Technical Services shall be contacted prior to commencement. VALSPAR PAINT (AUSTRALIA) PTY LTD (ABN 40 000 035 914)