

DURANAMEL® PR9

P10.03

Description

A single pack fast air drying, high build modified alkyd zinc phosphate primer.

Product Characteristics

- Excellent corrosion resistance.
- Quick drying.
- High build achievable in one coat application.
- Excellent adhesion to suitably prepared steel surfaces.
- Suitable for top coating with Wattyl Protective Coatings' enamel product range for both new and maintenance work.
- May be overcoated with selected coloured two-pack products including Poly U400, Poly U750, Colourthane C-Series and Paracryl IF540 when applied direct to mild steel.

Colours and Gloss

Grey, red oxide, blue, mustard yellow – flat.

Recommended Film Thickness (Per Coat)

	Minimum	Maximum	Typical
Dry film thickness (µm)	50	75	50
Wet film thickness (µm)	120	180	120
Theoretical spreading rate (m ² /l)	8.4	5.6	8.4

Basic Data at 25°C

Solids content approx.	42% by volume
Touch dry after	15 minutes
Full cure	5 days
Temperature resistance	125°C (dry)

Surface Preparation

- All surfaces to be coated must be clean, dry and free from chalking and contamination.
- Oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning.

MILD STEEL

- Blast clean in accordance with AS 1627.4 to Sa 2½ minimum (AS 1627.9), surface profile 35-50 microns.
- If oxidation occurs between blasting and application, the surface should be reblasted to the specified visual standard.
- Surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner.
- Power tool clean in accordance with AS 1627.2 to St 2 minimum (AS 1627.9).

PREVIOUS SUITABLE COAT

- Dry and free from chalking and contamination and sufficiently roughened if necessary.
- Substrate temperature must be at least 3°C above dew
- Relative humidity should not exceed 85%.

Application Instructions

- Stir well before use with a flat bladed stirrer or mechanical mixer.
- The temperature of the paint must be above 15°C, otherwise extra thinner may be required to obtain application viscosity.
- Too much thinner will result in lower sag resistance and slower cure.
- Adequate ventilation must be continuously maintained during application and curing.
- Wattyl recommends the use of coating inspection reports in compliance with AS/NZS 3894.10,11,12 refer to Information Sheet I-20 for more information.
- For recommendations outside those contained in this data sheet, refer to Wattyl.

Application Methods

	AIRLESS SPRAY	AIR SPRAY	BRUSH/ROLLER For spot repair and stripe coating only
Recommended thinner	Thinner L700	Thinner L700	Mineral Turps
Volume of thinner	0-3%	0 -10%	0-5%
Nozzle orifice approx.	0.46mm (0.018 inch)	1.8 - 2.0mm	The maximum dry film thickness that can be achieved when brushing/rolling is 40 microns.
Nozzle pressure	15 MPa (2100 psi)	0.3 - 0.4 MPa (50 - 60 psi)	Multiple coats may be required to achieve the recommended dry film thickness.

CLEANING SOLVENT | Thinner L700

Safety Precautions

- Flammable. Avoid contact with heat and naked flame.
- Avoid contact with skin and eyes.
- Use gloves, mask and goggles during application.
- Provide adequate ventilation when using in confined spaces.
- This product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the safety data sheet (SDS).

DURANAMEL® PR9

P10.03

Additional Data

OVERCOATING TABLE

Minimum and maximum overcoating intervals with:
Duranamel PR9, Duranamel BR22, All Purpose Enamel, Agricultural Enamel.

Interval	5°C	15°C	25°C	35°C
Min	8 hrs	6 hrs	4 hrs	2 hrs
Max	Unlimited			

* Ensure surface is dry and free of chalking and contamination.

Minimum and maximum overcoating intervals with:
Poly U400, Poly U750, Paracryl IF540 and Colourthane C-Series.

Interval	5°C	15°C	25°C	35°C
Min	16 hrs	10 hrs	6 hrs	3 hrs
Max	Unlimited			

* Ensure surface is dry and free of chalking and contamination.

CURING TABLE

Paint temperature	5°C	15°C	25°C	35°C
Dry to handle	5 hrs	3 hrs	2 hrs	1 hr
Full cure	10 days	7 days	5 days	3 days

* Adequate ventilation must be continuously maintained during application and curing.

Precautions

For recommendations outside those contained in this data sheet, refer to Wattyl.

Product Compatibility

TOPCOATS

- Duranamel BR22
- All Purpose Enamel
- Agricultural Enamel
- Poly U400 (colours)
- Poly U750 (colours)
- Paracryl IF540 (colours)
- Colourthane C-Series (colours)

Storage and Packaging

- Shelf life at least 12 months 25°C.
- All components shall be stored in a dry internal environment at between 5°C and 35°C.
- Packaging: 20 litres (all colours), 4 and 200 litres (grey only- made to order)
- Product line: 2002

For the most up to date information, please visit our website at www.wattylpc.com.au, or contact us at Australia 132 101 (Australia) 0800 825 7727 (New Zealand).

This information, provided by Hempel (Wattyl) Australia Pty Ltd is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Wattyl's warranties express and implied. Wattyl advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Wattyl and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl office before using the product(s). 4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Wattyl's Technical Services shall be contacted prior to commencement. Trademarks are the property of Hempel (Wattyl) Australia Pty Ltd. (ABN 40 000 035 914)

Wattyl Protective Coatings is part of the Hempel Group, a world leading supplier of trusted coating solutions. Hempel is a global company with strong values, working with customers in the decorative, marine, infrastructure and energy industries. Our purpose is to shape a brighter future with sustainable coating solutions, and with more than 100 years of protecting some of our customer's most valuable assets, we aim to earn their trust every day. The Hempel Group is proudly owned by the Hempel Foundation.